



Chip Encapsulants For Superior Protection on Flexible and Rigid Platforms

Dymax 9000-series encapsulants cure in seconds upon exposure to UV/ Visible light and are easily incorporated into automated systems for maximizing microelectronic assembly and production speeds. These tough, flexible encapsulants have high ionic purity, resistance to humidity, and resistance to thermal shock to effectively protect components and improve their reliability. 9000-series single-component encapsulants contain no sharp, abrasive, mineral or glass fillers to abrade fine wires, and their combination of low Tg and low modulus means low stress. They have excellent adhesion to Polyimide, PET, flexible printed circuits, FR4, and ceramic boards and provide superior protection for glob top and chip-on-board applications. 9000-series encapsulants are also ideal for encapsulating ICs on flex circuits. The encapsulants are available in a wide range of viscosities, from thin to nonflowing gel, and several grades are formulated with secondary moisture cure to ensure the material cures in shadowed areas.



- Tack-free UV/Visible light cure in seconds
- Secondary moisture cure available for curing in shadow areas
- 100% solvent free
- High ionic purity
- Resistance to thermal shock and moisture
- · Low stress under thermal cycle
- · Electrically insulating
- Very low VOCs
- High coverage

Cost Savings of Dymax Encapsulants

- Cure in seconds; increase throughput
- Minimal floor space requirements
- Simple to dispense
- Eliminate labor costs associated with complex dispensing system maintenance and manual transferring of parts for long cure

Product	UV/Visible Light	Heat	Moisture	Features	Nominal Viscosity, cP (20 rpm)	Durometer Hardness	Modulus of Elasticity, MPa [psi]	Elongation at Break, %
9-20558-REV-A	•	•		Secondary heat cure; flexible; bonds well to FPCs	24,000	D35	2.3 [340]	160
9001-E-V3.0	•	•		Secondary heat cure; moisture and thermal cycling resistance; well suited for chip-on-board, chip-on-flex, and multi-chip modules	400	D45	17.2 [2,500]	150
9001-E-V3.1					4,500			
9008	•			Remains flexible at low temperatures; high moisture resistance	4,500	D35	45 [6,500]	270
9014	•		•	Secondary moisture cure for shadow areas; flexible; blue fluorescing	12,500	A70	119 [17,300]	63
9037-F	•	•		Secondary heat cure for shadow areas; flexible; blue fluorescing; moisture and thermal resistance	50,000	D40	6.2 [900]	110
9101	•		•	Secondary moisture cure for shadow areas; flexible; moisture and thermal resistant	7,000	D30-D50	17.5 [2,550]	38
9102					17,000		18.4 [2,670]	34
9103					25,000		17.6 [2,560]	36



Typical Ionic Content								
Extractable Chloride	<10 ppm	IC						
Sodium	<10 ppm	ICP						
Potassium	<10 ppm	AA						
Fluoride	<10 ppm	IC						

Curing Options for Dymax Encapsulants

Dymax encapsulants cure in seconds upon exposure to UV light, affording the fastest processing possible. Avoid processing bottlenecks by choosing an efficient and cost-effective Dymax encapsulant with a matched Dymax UV light-curing system.



www.dymax.com

Americas USA | +1.860.482.1010 | info@dymax.com

@2003-2021 Dymax Corporation, All rights reserved. All trademarks in this guide, except where noted, are the property of, or used under license by, Dymax Corporation, U.S.A.

Europe Germany | +49 611.962.7900 | info_de@dymax.com Ireland | +353 21.237.3016 | info_ie@dymax.com

Asia

Singapore | +65.67522887 | info_ap@dymax.com China | +86.755.83485759 | dymaxasia@dymax.com Hong Kong | +852.2460.7038 | dymaxasia@dymax.com Korea | +82.31.608.3434 | info_kr@dymax.com

Technical data provided is of a general nature and is based on laboratory test conditions. Dymax Europe GmbH does not warrant the data contained in this bulletin. Any warranty applicable to products, its application and use is strictly limited to that contained in Dymax Europe GmbH does not assume any responsibility for test or performance results obtained by users. It is the user's responsibility to determine the suitability for the product application and purposes and the suitability for user's intended manufacturing apparatus and methods. The user should adopt such precautions and use guidelines as may be reasonably advisable or necessary for the protection of property and persons. Nothing in this bulletin shall act as a representation that the product use or application will not infringe a patent owned by someone other than Dymax Corporation or act as a grant of license under any Dymax Corporation Patent. Dymax Europe GmbH recommends that each user adequately test its proposed use and application of the products before actual repetitive use, using the data contained in this bulletin as a general guide. AB012EU 9/29/2021