



## 9202-W

### Precision Positioning Optical Adhesive

#### APPLICATIONS

- Optical Alignment Where Minimal or No Movement is Required

#### FEATURES

- UV/Visible Light Cure
- High-Strength Positioning Adhesive
- Low Outgassing
- Low Shrinkage
- Low Moisture Absorption
- Opaque
- Heat-Cycle Stable
- Non-Movement During Cure or Thermal Excursions
- Complete Cure in Seconds
- Skin-friendly (IBOA Free)

#### RECOMMENDED SUBSTRATES

- Glass
- Metal
- Ceramic
- FR-4
- Polycarbonate

Dymax 9202-W is a low-shrinkage, low-outgassing, low-CTE adhesive designed for the precise positioning of lenses, prisms, and other optical components. 9202-W cures by exposure to ultraviolet and/or visible cure light. Dymax high-performance optical adhesives cure upon exposure to UV or visible light in seconds. Because of their solvent-free and rapid-cure features, they increase productivity, lower assembly cost and enhance worker safety. When cured with Dymax spot, beam, or flood lamps, they deliver optimum speed and performance for a variety of optical applications. This product is in full compliance with RoHS directives 2015/863/EU.

#### TYPICAL UNCURED PROPERTIES \*

Property	Value	Test Method
Solvent Content	None - 100% Solids	N/A
Appearance	Opaque	N/A
Viscosity, cP	260,000 (nominal)	ASTM D2556
Chemical Class	Acrylate	N/A
Soluble in	Organic Solvents	N/A
Density, g/ml	1.59	ASTM D1875
Shelf Life at Recommended Conditions from Date of Manufacture	6 months	N/A

#### TYPICAL CURED PROPERTIES \*

Property	Value	Test Method
Linear Shrinkage During Cure	0.5%	ASTM D2566
Durometer Hardness	D88	ASTM D2240
Elongation at Break	1.0%	ASTM D638
Tensile at Break	5,200 psi	ASTM D638
Modulus of Elasticity	611,150 psi	ASTM D638
CTE $\alpha_1$ , $\mu\text{m}/\text{m}/^\circ\text{C}$	45	ASTM E831
CTE $\alpha_2$ , $\mu\text{m}/\text{m}/^\circ\text{C}$	110	ASTM E831
Glass Transition Tg, $^\circ\text{C}$	122	ASTM D5418

#### OTHER CURED PROPERTIES \*

Property	Value	Test Method
Boiling Water Absorption, % (2 h)	0.4	ASTM D570

#### ADHESION

Substrate	Recommendation
ABS (acrylonitrile-butadiene-styrene)	✓
CAP (cellulose acetate propionate)	✓
PA6 polyamide (Nylon 6)	✓
PCB (Printed Circuit Board) (FR-4)	✓
PS (polystyrene)	✓
PVC poly(vinyl chloride), rigid	✓
PVC poly(vinyl chloride), flexible	✓

✓ Recommended      ◦ Limited Applications  
 st Requires Surface Treatment (e.g. plasma, corona treatment, etc.)

\* Not Specifications  
 N/A Not Applicable





## CURING GUIDELINES

Fixture time is defined as the time to develop a shear strength of 0.1 N/mm<sup>2</sup> [10 psi] between glass slides. Actual cure time typically is 3-to-5 times fixture time.

Dymax Curing System (Intensity)	Fixture Time or Belt Speed <sup>A</sup>
5000-ECE (200 mW/cm <sup>2</sup> ) <sup>B</sup>	15 s
BlueWave® 200 (10 W/cm <sup>2</sup> ) <sup>B</sup>	1 s
UVCS Conveyor with Fusion F300S (2.5 W/cm <sup>2</sup> ) <sup>C</sup>	3.0 m/min [10 ft/min]
BlueWave® MX-150 PrimeCure® 385 nm (15 W/cm <sup>2</sup> ) <sup>B</sup>	30 s

<sup>A</sup> Fixture times/belt speeds are typical for curing thin films through 100% UV and light-transmitting substrates. Light-obstructing substrates may require longer cure times.

<sup>B</sup> Intensity was measured over the UVA range (320-395 nm) using a Dymax ACCU-CAL™ 50 Radiometer.

<sup>C</sup> At 53 mm [2.1 in] focal distance. Maximum speed of conveyor is 8.2 m/min [27 ft/min]. Intensity was measured over the UVA range (320-395 nm) using the Dymax ACCU-CAL™ Radiometer.

Full cure is best determined empirically by curing at different times and intensities, and measuring the corresponding change in cured properties such as tackiness, adhesion, hardness, etc. Full cure is defined as the point at which more light exposure no longer improves cured properties.

Dymax recommends that customers employ a safety factor by curing longer and/or at higher intensities than required for full cure. Although Dymax Application Engineering can provide technical support and assist with process development, each customer must ultimately determine and qualify the appropriate curing parameters required for their unique application.

## DISPENSING SUPPORT

The Dymax Application Engineering team is ready to discuss your application requirements to provide the most appropriate dispensing and/or spraying solution. Visit our current dispensing equipment portfolio [here](#) or consult our [global contact](#) phone numbers and online chat feature (available in North America only) during normal business hours for instant support.

## STORAGE AND SHELF LIFE

Store material in a cool, dark place when not in use. Do not expose to UV light or sunlight. Material may polymerize upon prolonged exposure to ambient light. Replace lid immediately after use. This material shelf life noted on page 1 of this document, when stored between 10°C (50°F) and 32°C (90°F) in the original, unopened container.



## GENERAL INFORMATION

This product is intended for industrial use only. Keep out of the reach of children. Avoid breathing vapors. Avoid contact with skin, eyes, and clothing. Wear impervious gloves. Repeated or continuous skin contact with uncured material may cause irritation. Remove material from skin with soap and water. Never use organic solvents to remove material from skin and eyes. For more information on the safe handling of this material, please refer to the Safety Data Sheet before use.

The data provided in this document are based on historical testing that Dymax performed under laboratory conditions as they existed at that time and are for informational purposes only. The data are neither specifications nor guarantees of future performance in a particular application. Dymax does not guarantee that this product's properties are suitable for the user's intended purpose.

Numerous factors—including, without limitation, transport, storage, processing, the material with which the product is used, and the ultimate function or purpose for which the product was obtained—may affect the product's performance and/or may cause the product's actual behavior to deviate from its behavior in the laboratory. None of these factors are within Dymax's control. Conclusions about the behavior of the product under the user's particular conditions, and the product's suitability for a specific purpose, cannot be drawn from the information contained in this document.

It is the user's responsibility to determine (i) whether a product is suitable for the user's particular purpose or application and (ii) whether it is compatible with the user's intended manufacturing process, equipment, and methods. Under no circumstances will Dymax be liable for determining such suitability or compatibility. Before the user sells any item that incorporates Dymax's product, the user shall adequately and repetitively test the item in accordance with the user's procedures and protocols. Unless specifically agreed to in writing, Dymax will have no involvement in, and shall under no circumstances be liable for, such testing.

Dymax makes no warranties, whether express or implied, concerning the merchantability of this product or its fitness for a particular purpose. Nothing in this document should be interpreted as a warranty of any kind. Under no circumstances will Dymax be liable for any injury, loss, expense or incidental or consequential damage of any kind allegedly arising in connection with the user's handling, processing, or use of the product. It is the user's responsibility to adopt appropriate precautions and safeguards to protect persons and property from any risk arising from such handling, processing, or use.

The specific conditions of sale for this product are set forth in Dymax's [General Terms & Conditions of Sale](#). Nothing contained herein shall act as a representation that the product use or application is free from patents owned by Dymax or any others. Nothing contained herein shall act as a grant of license under any Dymax Corporation Patent.

Except as otherwise noted, all trademarks used herein are trademarks of Dymax. The "®" symbol denotes a trademark that is registered in the U.S. Patent and Trademark Office.

The contents of this document are subject to change. Unless specifically agreed to in writing, Dymax shall have no obligation to notify the user about any change to its content.

## CONTACT DYMAYX

[www.dymax.com](http://www.dymax.com)

### Americas

USA | +1.860.482.1010 | [info@dymax.com](mailto:info@dymax.com)

### Europe

Germany | +49 611.962.7900 | [info\\_de@dymax.com](mailto:info_de@dymax.com)

Ireland | +353 21.237.3016 | [info\\_ie@dymax.com](mailto:info_ie@dymax.com)

### Asia

Singapore | +65.67522887 | [info\\_ap@dymax.com](mailto:info_ap@dymax.com)

Shenzhen | +86.755.83485759 | [info@hanarey.com](mailto:info@hanarey.com)

Hong Kong | +852.2460.7038 | [dymaxasia@dymax.com](mailto:dymaxasia@dymax.com)

Korea | +82.31.608.3434 | [info\\_kr@dymax.com](mailto:info_kr@dymax.com)