



SpeedMask® 730-BT

Chemical and Harsh-Environment Processing Maskant

APPLICATIONS

- Plating
- Anodizing
- Grit Blasting
- Shot Peening
- Sand Blasting
- Orthopedic Implant Protection

FEATURES

- UV/Visible Light Cure
- Excellent Surface Protection
- Excellent Chemical Resistance
- Fast Curing
- Easy Peel Off
- Spray or Dip
- High-Visibility Blue Color
- Trimmable After Cure
- Acid Resistant (Nitric, Sulfuric, and Hydrochloric)
- ISO 10933-5 Cytotoxicity

RECOMMENDED SURFACES

- Nickel Alloys
- Steel
- Titanium
- Stainless Steel
- Aluminum
- Glass

SpeedMask® 730-BT UV/Visible light-curable masking resin is formulated to provide good surface protection during plating, anodizing, and aggressive grit-blasting operations. It aids the manufacture, overhaul, repair, and rework of turbine engine blades, vanes, and other turbine components. 730-BT is impervious to most acid solutions. When properly cured, 730-BT leaves no residue on non-porous surfaces. This 100% organic resin cures quickly. The removal of the cured maskant can be aided with the use of a hand tool (plastic, anti-static or metal), heat aided to localize area, an ultrasonic bath, dry ice blast or embrittlement, water jet blast, incineration, when applicable or automated grippers. Please reach out to Dymax Application Engineering for details on these removal options. SpeedMask resins contain no nonreactive solvents and cure upon exposure to light. Their ability to cure in seconds enables faster processing, greater output, and lower processing costs. When cured with Dymax light-curing spot lamps, focused-beam lamps, or flood lamps, it delivers optimum speed and performance for many masking applications. Dymax lamps offer the ideal balance of UV and visible light for the fastest, deepest cures. This product is in full compliance with RoHS directives 2015/863/EU.

UNCURED PROPERTIES *

Property	Value	Test Method
Solvent Content	No Nonreactive Solvents	N/A
Chemical Class	Acrylated Urethane	N/A
Appearance	Blue Translucent Gel	N/A
Soluble in	Organic Solvents	N/A
Density, g/ml	0.96	ASTM D1875
Viscosity, cP (20 rpm)	22,000 (nominal)	ASTM D2556
Shelf Life at Recommended Conditions from Date of Manufacture	12 months	N/A

CURED MECHANICAL PROPERTIES *

Property	Value	Test Method
Durometer Hardness	D35	ASTM D2240
Tensile at Break, MPa [psi]	4.8 [700]	ASTM D638
Elongation at Break, %	300	ASTM D638
Modulus of Elasticity, MPa [psi]	3.4 [500]	ASTM D638

DISPENSE EQUIPMENT RECOMMENDATIONS *

Application	Manual	Semi-Automated	Fully Automated
Dots	SD-100	Model 400 Needle Valve	eco-PEN
Beads	SD-100	Model 400 Needle Valve	eco-PEN
Large Area	SG-150-RH	SG-150-RH	eco-SPRAY

CURING EQUIPMENT RECOMMENDATIONS *

Process Method	Spot Lamp	Flood Lamp	Conveyor
LED Curing/Wavelength	BlueWave® MX-150 PrimeCure® (385 nm)	BlueWave® AX-550 PrimeCure® (385 nm)	UVCS Conveyor with 385 nm LED Flood
Broad Spectrum	BlueWave® 200	5000-ECE or PortaRay 400	UVCS Conveyor with Fusion F300S

* Not Specifications

N/A Not Applicable

© 2023 Dymax Corporation. All rights reserved.

All trademarks in this guide, except where noted, are the property of, or used under license by Dymax Corporation, U.S.A.

Technical Data Collected PRIOR TO 2008 Rev. 02/10/2023





OTHER CURED PROPERTIES *		
Property	Value	Test Method
Boiling Water Absorption, % (2 hr)	0.2	ASTM D570
Water Absorption, % (25°C, 24 h)	0.3	ASTM D570
Linear Shrinkage, %	1.2	ASTM D2566

CURING GUIDELINES

Cure rate is dependent upon many variables, including lamp intensity, distance from the light source, and required depth of cure. The cure times below are based on lab results and are intended for reference only. Testing was performed using a 0.38 mm [0.015 in] coating thickness. Time/belt speed was determined by a complete, tack-free cure.

Dymax Curing System (Intensity)	Cure Time or Belt Speed
2000-EC (50 mW/cm ²) ^A	10 s
5000-EC (200 mW/cm ²) ^A	4 s
BlueWave® LED Flood PrimeCure® (575 mW/cm ²) ^B	8 s
PortaRay 400 (400 mW/cm ²) ^A	1 s
UVCS Conveyor with Fusion F300S (2.5 W/cm ²) ^C	8.2 m/min [27 ft/min]
BlueWave® 200 (10 W/cm ²) ^A	0.4 s

^A Intensity was measured over the UVA range (320-395 nm) using a Dymax ACCU-CAL™ 50 Radiometer.

^B Intensity was measured over the light range of 350-450 nm using a Dymax ACCU-CAL™ 50-LED Radiometer.


^C At 53 mm [2.1 in] focal distance. Maximum speed of conveyor is 8.2 m/min [27 ft/min]. Intensity was measured over the UVA range (320-395 nm) using a Dymax ACCU-CAL™ 160 Radiometer.

Full cure is best determined empirically by curing at different times and intensities, and measuring the corresponding change in cured properties such as tackiness, adhesion, hardness, etc. Full cure is defined as the point at which more light exposure no longer improves cured properties. Higher intensities or longer cure times may degrade Dymax light-curable maskants.

Dymax recommends that customers employ a safety factor by curing longer and/or at higher intensities than required for full cure. Although Dymax Application Engineering can provide technical support and assist with process development, each customer must ultimately determine and qualify the appropriate curing parameters required for their unique application.

DEPTH OF CURE

The graph below shows the increase in depth of cure as a function of exposure time. A 9.5 mm [0.37 in] diameter specimen was cured in a polypropylene mold and cooled to room temperature. It was then released from the mold and the cure depth was measured.





OPTIMIZING PERFORMANCE AND HANDLING

1. This product cures with exposure to UV and visible light. Exposure to ambient and artificial light should be kept to a minimum before curing. Dispensing components, including needles and fluid lines, should be 100% light blocking, not just UV blocking.
2. All surfaces to be masked should be clean and free from grease, mold release, or other contaminants prior to dispensing the resin.
3. Oxygen in the atmosphere may inhibit surface cure. Surfaces exposed to air may require higher intensity UV (>100 mW/cm²) to produce a tack-free cure. Flooding the bond area with an inert gas, such as nitrogen, can also reduce the effects of oxygen inhibition.
4. Part should be allowed to cool after cure before testing.
5. Light curing generally produces some heat. If necessary, cooling fans can be placed in the curing area to reduce the heating effect on components.
6. At the point of curing, an air exhaust system is recommended to dissipate any heat and vapors formed during the curing process.
7. Cure speed is dependent upon many variables, including lamp intensity, distance from the light source, required depth of cure, bond gap, and percent light transmission of the substrate.

DISPENSING SUPPORT

The Dymax Application Engineering team is ready to discuss your application requirements to provide the most appropriate dispensing and/or spraying solution. Visit our current dispensing equipment portfolio [here](#) or consult our [global contact](#) phone numbers and online chat feature (available in North America only) during normal business hours for instant support.

STORAGE AND SHELF LIFE

Store the material in a cool, dark place when not in use. Do not expose to light. This product may polymerize upon prolonged exposure to ambient and artificial light. Keep covered when not in use. This material shelf life is noted on page 1 of this document, when stored between 10°C (50°F) and 32°C (90°F) in the original, unopened container.

CLEAN UP

Uncured material may be removed from dispensing components and parts with organic solvents. Cured material will be impervious to many solvents and difficult to remove. Cleanup of cured material may require mechanical methods such as ultrasonic bath, water jet, vacuum tweezers, air knife and/or warming to aid in the removal.

BIOCOMPATIBILITY

Polymerized Dymax SpeedMask® maskants are biocompatibility tested in accordance with ISO 10993. The completed tests are listed on each product data sheet. Copies of the test reports are available upon request. In all cases, it is the user's responsibility to determine and validate the suitability of these materials for the intended use. These materials have not been tested for prolonged or permanent implantation and are only intended for use in short-term (<29 days), single-use disposable-device, or removable applications. Dymax does not authorize their use in long-term implant applications. Customers using these materials for such applications do so at their own risk and take full responsibility for ensuring product safety and biocompatibility.



SPEEDMASK® MASKING RESINS 730-BT Product Data Sheet

GENERAL INFORMATION

This product is intended for industrial use only. Keep out of the reach of children. Avoid breathing vapors. Avoid contact with skin, eyes, and clothing. Wear impervious gloves. Repeated or continuous skin contact with uncured material may cause irritation. Remove material from skin with soap and water. Never use organic solvents to remove material from skin and eyes. For more information on the safe handling of this material, please refer to the Safety Data Sheet before use.

The data provided in this document are based on historical testing that Dymax performed under laboratory conditions as they existed at that time and are for informational purposes only. The data are neither specifications nor guarantees of future performance in a particular application. Dymax does not guarantee that this product's properties are suitable for the user's intended purpose.

Numerous factors—including, without limitation, transport, storage, processing, the material with which the product is used, and the ultimate function or purpose for which the product was obtained—may affect the product's performance and/or may cause the product's actual behavior to deviate from its behavior in the laboratory. None of these factors are within Dymax's control. Conclusions about the behavior of the product under the user's particular conditions, and the product's suitability for a specific purpose, cannot be drawn from the information contained in this document.

It is the user's responsibility to determine (i) whether a product is suitable for the user's particular purpose or application and (ii) whether it is compatible with the user's intended manufacturing process, equipment, and methods. Under no circumstances will Dymax be liable for determining such suitability or compatibility. Before the user sells any item that incorporates Dymax's product, the user shall adequately and repetitively test the item in accordance with the user's procedures and protocols. Unless specifically agreed to in writing, Dymax will have no involvement in, and shall under no circumstances be liable for, such testing.

Dymax makes no warranties, whether express or implied, concerning the merchantability of this product or its fitness for a particular purpose. Nothing in this document should be interpreted as a warranty of any kind. Under no circumstances will Dymax be liable for any injury, loss, expense or incidental or consequential damage of any kind allegedly arising in connection with the user's handling, processing, or use of the product. It is the user's responsibility to adopt appropriate precautions and safeguards to protect persons and property from any risk arising from such handling, processing, or use.

The specific conditions of sale for this product are set forth in Dymax's [General Terms & Conditions of Sale](#). Nothing contained herein shall act as a representation that the product use or application is free from patents owned by Dymax or any others. Nothing contained herein shall act as a grant of license under any Dymax Corporation Patent.

Except as otherwise noted, all trademarks used herein are trademarks of Dymax. The "®" symbol denotes a trademark that is registered in the U.S. Patent and Trademark Office.

The contents of this document are subject to change. Unless specifically agreed to in writing, Dymax shall have no obligation to notify the user about any change to its content.

CONTACT DYMAX

www.dymax.com

Americas

USA | +1.860.482.1010 | info@dymax.com

Europe

Germany | +49 611.962.7900 | info_de@dymax.com

Ireland | +353 21.237.3016 | info_ie@dymax.com

Asia

Singapore | +65.67522887 | info_ap@dymax.com

Shenzhen | +86.755.83485759 | dymaxasia@dymax.com

Hong Kong | +852.2460.7038 | dymaxasia@dymax.com

Korea | +82.31.608.3434 | info_kr@dymax.com