

Suggested Method for Spray Application of 984-LVUF Conformal Coatings and Similar Low-Viscosity Dymax Products

SPRAY EQUIPMENT

BINKS Model 98-1131*

- MACH 1 HVLP Spray Gun
- 95-P Air Nozzle
- 94 Fluid Nozzle
- 50 oz Pressure Cup

PRESSURE SETTINGS TO SPRAY LOW-VISCOSITY COATINGS

- Pressure Pot - 6-8 psi
- Gun Inlet Spray Pressure - 30-40 psi
- Air Nozzle Spray Pressure - 2-3 psi

Refer to BINKS Manufacturing Company on the appropriate spray booth and exhaust for your application.

This recommended hand spray method can be incorporated with a moderate- to high-intensity curing system which is available through Dymax Corporation.

For further information, contact Dymax Applications Engineering or Equipment Engineering.

* all stainless steel construction

© 1997-2010 Dymax Corporation. All rights reserved. All trademarks in this guide, except where noted, are the property of, or used under license by Dymax Corporation, U.S.A.

The data contained in this bulletin is of a general nature and is based on laboratory test conditions. Dymax does not warrant the data contained in this bulletin. Any warranty applicable to the product, its application and use is strictly limited to that contained in Dymax's standard Conditions of Sale. Dymax does not assume responsibility for test or performance results obtained by users. It is the user's responsibility to determine the suitability for the product application and purposes and the suitability for use in the user's intended manufacturing apparatus and methods. The user should adopt such precautions and use guidelines as may be reasonably advisable or necessary for the protection of property and persons. Nothing in this bulletin shall act as a representation that the product use or application will not infringe a patent owned by someone other than Dymax or act as a grant of license under any Dymax Corporation Patent. Dymax recommends that each user adequately test its proposed use and application before actual repetitive use, using the data contained in this bulletin as a general guide.

LIT139 2/01/1998

Dymax Corporation
860.482.1010
info@dymax.com
www.dymax.com

Dymax Oligomers & Coatings
860.626.7006
oligomers&coatings@dymax.com
www.dymax-oc.com

Dymax Europe GmbH
+49 (0) 611.962.7900
info_de@dymax.com
www.dymax.de

Dymax UV Adhesives &
Equipment (Shenzhen) Co Ltd
+86.755.83485759
dymaxasia@dymax.com
www.dymax.com.cn

Dymax UV Adhesives &
Equipment (Shanghai) Co Ltd
+86.21.37285759
dymaxasia@dymax.com
www.dymax.com.cn

Dymax Asia (H.K.)
Limited
+852.2460.7038
dymaxasia@dymax.com
www.dymax.com.cn

Dymax Korea LLC
82.2.784.3434
info@dymax.kr
www.dymax.co.kr